

WMP-ASJ

POLYPROPYLENE / CORE / SCRIM / FOIL

TENTATIVE SPECIFICATION

Meets ASTM C1136, Type I, II, III, IV

| FACING COMPOSITION | DESCRIPTION | VALUES (ENGLISH) | VALUES (METRIC) |
|--------------------|-------------------------------|--------------------------------|--------------------------------------|
| White Film | Polypropylene | 0.0015 inch | 38.1 micron |
| Adhesive | Flame Resistant | | |
| Core | Proprietary | 38 lbs / 3000 ft ² | 62 g / m ² |
| Adhesive | Fire Retardant | | |
| Reinforcing | Tri-directional Fiberglass | 5 / inch (MD) 5 / inch (XD) | 20 / 100 mm (MD) 20 / 100 mm (XD) |
| Barrier Coating | Polymeric | | |
| Foil | Aluminum | 0.0003 inch | 7.6 micron |

| PHYSICAL PROPERTIES | TEST METHOD | VALUES (ENGLISH) | VALUES (METRIC) |
|-----------------------------|-----------------------------------|--|--------------------------------------|
| Basis Weight | Scale | 34 lbs / 1000 ft ² | 166 g / m ² |
| Permeance (WVTR) | ASTM E96 Procedure A | 0.02 perm (grains/hrft ² in Hg) | 1.15 ng / N's |
| Bursting Strength | ASTM D774 | 120 psi | 8.4 kg / cm ² |
| Puncture Resistance | ASTM C1136 | 60 beach units | 1.8 Joules |
| Tensile Strength | ASTM C1136 | 80 lbs/inch width (MD) 60 lbs/inch width (XD) | 14.0 kN / m (MD) 10.5 kN / m (XD) |
| Caliper / Thickness | Micrometer | 0.009 inch | 229 micron |
| Accelerated Aging | 30 Days @ 95% RH, 120°F (49°C) | No Corrosion No Delamination | No Corrosion No Delamination |
| Low Temperature Resistance | ASTM D1790 -40°F (-40°C) | Remains Flexible No Delamination | Remains Flexible No Delamination |
| High Temperature Resistance | 4 hours @ 240°F (116°C) | Remains Flexible No Delamination | Remains Flexible No Delamination |
| Water Immersion | 24 hours @ 73°F (23°C) | No Delamination | No Delamination |
| Mold Resistance | ASTM C665 / C1338 | No Growth | No Growth |
| Dimensional Stability | ASTM D1204 | 0.25% | 0.25% |

| FIRE TESTING | ASTM E84 |
|-----------------|----------------------------|
| | Polypropylene Side Exposed |
| Flame Spread | 10 |
| Smoke Developed | 30 |

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

5010 River Road Mount Bethel, Pennsylvania 18343-5610 U.S.A.
Phone: (570) 897-8200 Fax: (570) 897-6081 Web: www.lamtec.com