

3035 BLACK

BLACK COATING / FOIL / SCRIM / KRAFT

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Black Coating	Flame Resistant	0.0002"	5.1 micron
Foil	Aluminum	0.0003 inch	7.6 micron
Barrier Coating	Elastomeric Polymer	0.0001 inch	2.5 micron
Reinforcing	Tri-directional Fiberglass	2 / inch (MD) 3 / inch (XD)	8 / 100 mm (MD) 12 / 100 mm (XD)
Adhesive	Emulsion		
Kraft	Natural	30 lbs. / 3000 ft ²	49 g / m ²

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	21 lbs / 1000 ft ²	103 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hrft ² in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	40 psi	2.8 kg / cm ²
Puncture Resistance	ASTM C1136	25 beach units	0.7 Joules
Tensile Strength	ASTM C1136	40 lbs/inch width (MD) 25 lbs/inch width (XD)	7.0 kN / m (MD) 4.4 kN / m (XD)
Caliper / Thickness	Micrometer	0.007 inch	178 microns
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%

FIRE TESTING	ASTM E84
Flame Spread	Black Coating Side 0
Smoke Developed	0

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

"LAMTEC" AND "WMP" ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Lamtec Corporation 700 Bartley-Chester Road P.O. Box 37 Flanders, New Jersey 07836-0037 USA

Phone: (973) 584-5500 (800) 852-6832

Fax: (973) 584-5178 (888) 852-6832